

## DICHROIC

# DCH 426

### INSIDE APPLICATION



Blue / Red glints

### DICHROIC FILM

This film lets light in and captures it to form different colors reflections. The reflections vary from blue to red. Depending on your viewing angle, these visual effects form unmatched nuances in terms of modern decoration.

### INFORMATION

**MATERIAL :** .....PET 51 microns  
**ADHESIVE :** .....Acrylate PSA 7 microns  
**LINER :** .....Siliconed PET 12 microns  
**TOTAL THICKNESS :** .....70 microns  
**COLOR :** .....Blue / Red glint  
**APPLICATION FACE :** .....Inside  
**UVA TRANSMISSION :** .....5 %  
**APPLICATION T° :** .....min, + 5°C  
**FIRE RATING :** ..... B-S1, D0  
**GUARANTEE :** .....5 years\*

### DIMENSION

1,38 x 2,5 m  
 1,38 x 5 m  
 1,38 x 10 m  
 1,38 x 30 m

\* For glazing not exposed to the sun



**Durability :** from 12 to 15 years for vertical application in central Europe.



**Use :** Réfectiv window films are designed for use on any type of clear normal glass.




**Maintenance after 30 days :** with usual cleaning solutions (non-abrasive, without ammonia...). Cleaning products that may scratch the film should be avoided.



**Storage :** 2 years from delivery. This film should be kept away from excessive humidity and sun rays, at temperatures below 38°C.

In order to constantly improve our production we may change a product colour and manufacturing process without prior notice.



#### Application's notice



#### Application's video



#### Application Method

The glass surface on which you want to apply the film has to be free from dust, grease or other contaminants. Some specific materials such as polycarbonate can cause air bubble problems. Therefore, a compatibility test is recommended. For more precision we recommend to refer back to the application table.

#### Production and standards

In order to constantly improve our production we may change a product colour and manufacturing process without prior notice. Before applying our products we recommend that our users ensure that the film is suitable for the intended use and comply with current standards.